



---

<b>Base Cloth:</b>	96% (min) Amorphous Silica
<b>Weave:</b>	Leno
<b>Coating:</b>	Phenolic Resin
<b>Mesh Size:</b>	1.5mm x 1.5mm – Style 1515 2.0mm x 2.0mm – Style 2020 2.0mm x 3.0mm – Style 2030
<b>Openings Per Inch:</b>	132/sq. in. – Style 1515 91/sq. in. – Style 2020 75/sq. in. – Style 2030
<b>Pouring Temperature:</b>	3000°F (1620°C)
<b>Pour Rates:</b>	10-25% Reduction (as compared to Unfiltered castings)
<b>Casting Load:</b>	Up to 300kg
<b>Applications:</b>	Castings for: Aluminum, Copper, Brass, Gray Iron Ductile Iron Permanent Mold, Centrifugal Casting, Ceramic Molding Investment Casting, Low Pressure Die Casting Lost Foam Shell, High Volume Green Sand (No Bake / V. Process)